

# Absecon Mills, Inc.

PO Box 672, Aloe & Vienna Avenues, Cologne, NJ USA

(T) 609-965-5373 (F) 609-965-7474

## Specification Sheet

<b>Pattern Number</b>	<b>D 10735</b>	<b>Date Issued</b>	<b>9/14/1986</b>
<b>Pattern Name</b>	<b>Sherpa</b>	Suitable for Railroading	
<b>Fiber Content</b>	100% Marquésa® Lana		
<b>Actual Weight</b>	16.0 ounces per linear yard (±1oz)	494 grams per linear meter (± 14 g)	
<b>Standard Width</b>	54" (137-140 cm)		
<b>Finish</b>	SBR		
<b>Repeat Size</b>	None Horizontal None Vertical	0.0 cm Horizontal	0.0 cm Vertical
<b>Test Cleaning Code</b>	WS - For water based stains use water based cleaning agent. For oil based stains use solvent cleaner.		

### Flame Resistance - Meets requirements of the following fire codes:

California Technical Bulletin 117, Section E  
 CS-191-53, Class 1  
 UFAC, Class 1  
 B.S. 5852 Part 1: 1979 Ignition Source 0; smouldering cigarette  
 BIFMA X5.7-1991  
 NFPA 260-1989, Class 1

### Fabrics can also be treated to meet these additional codes:

Boston Fire Dept. BFD IX-1  
 New York Port Authority  
 FMVSS 302  
 FAR 25.853(a) Appendix F, Part 1, (a)(I)(ii)

### Suitable for:

Corporate  
 Church  
 Hospitality  
 Healthcare  
 International  
 Transportation

Test Description	Test	Warp	Fill
Break Strength	ASTM-D-5034	300 lbs.	300 lbs.
Tear Strength	ASTM-D-2262	60 lbs.	63 lbs.
Seam Slippage	ASTM-D-4034	50 lbs.	54 lbs.
Elongation	JIFS	3.1 %	3.6 %
Dimensional Stability	ASTM-D-3597	1 %	0 %
Colorfastness to Crocking	AATCC 8	Wet:Class 5	Dry:Class 5
Colorfastness to Light	AATCC 16E	Class: 5 400 Hours	
Abrasion-Wyzenbeek (wire screen)	ASTM-D-4157	250,000+ Double Rubs	
Abrasion-Wyzenbeek (cotton duck)	ASTM-D-4157	Double Rubs	
Abrasion-Martindale	BS 5690	100,000+ Cycles	